

**ResMart Ultra GPPS 8-** Medium flow general purpose crystal polystyrene

Technical Data Sheet Properties

Physical Property	Value	Test Method
Transmittance	90 %	ASTM D 1003
Melt Flow Rate @ 200°C - 5kg	8.0 g/10 min	ASTM D 1238
Tensile Modulus	460,000 psi	ASTM D 638
Specific Gravity	1.04	ASTM D 792
Notched IZOD Impact Strength	0.30 ft-lb/in.	ASTM D256

\* Data herein is typical and not to be construed as specifications.

Regulatory Compliance

Regulatory Compliance	Value
FDA Compliance	Yes
RoHS Compliance	Yes

The information provided on this datasheet should only be used as a guideline. Actual lot to lot values will vary.

Disclaimer: No information supplied by ResMart LLC constitutes a warranty regarding product performance or use. Any information regarding performance or use is only offered as suggestion for investigation for use, based upon ResMart LLC or other customer experience. ResMart LLC makes no warranties, expressed or implied, concerning the suitability or fitness of any of its products for any particular purpose. It is the responsibility of the customer to determine that the product is safe, lawful and technically suitable for the intended use. The disclosure of information herein is not a license to operate under, or a recommendation to infringe any patents.