

ResMart Ultra RCoPP 12- Prime FDA Random Clarified Copolymer

Polypropylene that provides a good combination of impact and clarity

Technical Data Sheet Properties

Physical Property	Value	Test Method
Haze (1.3mm)	8 %	ASTM D 1003
Melt Flow Rate @ 230°C - 2160g	12 g/10min	ASTM D 1238
Notched Izod Impact 0.125"	1.3 ft-lbs/in	ASTM D 256
Tensile Strength	4100 psi	ASTM D 638
Tensile Elongation @ Yield	10 %	ASTM D 638
Specific Gravity	.901	ASTM D 792

* Data herein is typical and not to be construed as specifications.

Injection Molding Processing Guidelines

Setting	Value
Drying Temperature	175 °F
Mold Temperature	90 - 150 °F
Drying Time	2 Hours
Melt Temperature	375 - 450 °F
Injection Pressure	10000 - 15000 psi

* Desiccant type dryer required.

Regulatory Compliance

Regulatory Compliance	Value
FDA Compliance	Yes
RoHS Compliance	Yes

The information provided on this datasheet should only be used as a guideline. Actual lot to lot values will vary.

Disclaimer: No information supplied by ResMart LLC constitutes a warranty regarding product performance or use. Any information regarding performance or use is only offered as suggestion for investigation for use, based upon ResMart LLC or other customer experience. ResMart LLC makes no warranties, expressed or implied, concerning the suitability or fitness of any of its products for any particular purpose. It is the responsibility of the customer to determine that the product is safe, lawful and technically suitable for the intended use. The disclosure of information herein is not a license to operate under, or a recommendation to infringe any patents.