

**SKYPEL G172D- SKYPEL G172D**

Technical Data Sheet Properties

Physical Property	Value	Test Method
Melt Flow Rate @ 230°C - 2160g	13 g/10min	ASTM D 1238
Rockwell Hardness (Shore D)	72	ASTM D 2240
Notched Izod Impact 0.125"	0.0022 ft-lbs/in	ASTM D 256
Tensile Strength	6670 psi	ASTM D 638
Tensile Elongation at Break	420 %	ASTM D 638
Flexural Modulus (psi)	78300 psi	ASTM D 790

\* Data herein is typical and not to be construed as specifications.

The information provided on this datasheet should only be used as a guideline. Actual lot to lot values will vary.

Disclaimer: No information supplied by ResMart LLC constitutes a warranty regarding product performance or use. Any information regarding performance or use is only offered as suggestion for investigation for use, based upon ResMart LLC or other customer experience. ResMart LLC makes no warranties, expressed or implied, concerning the suitability or fitness of any of its products for any particular purpose. It is the responsibility of the customer to determine that the product is safe, lawful and technically suitable for the intended use. The disclosure of information herein is not a license to operate under, or a recommendation to infringe any patents.