

Sumipex® LW-2 - Sumipex® LW-2 High flow

Technical Data Sheet Properties

Physical Property	Value	Test Method
Melt Flow Rate @ 230°C - 3800g	15.1 g/10 min	ASTM D 1238
Notched Izod Impact 0.125"	0.8 ft-lbs/in	ASTM D 256
Tensile Strength	9430 psi	ASTM D 638
HDT (264 psi) Annealed	198 °F	ASTM D 648
Flexural Modulus (psi)	450 psi	ASTM D 790
Flexural Strength	16000 psi	ASTM D 790
Specific Gravity	1.19	ASTM D 792
Flame Rating	HB	UL 94

* Data herein is typical and not to be construed as specifications.

Injection Molding Processing Guidelines

Setting	Value
Drying Temperature	158 - 176 °F
Mold Temperature	140 - 185 °F
Drying Time	4 - 6 Hours
Melt Temperature	410 - 473 °F

* Desiccant type dryer required.

The information provided on this datasheet should only be used as a guideline. Actual lot to lot values will vary.

Disclaimer: No information supplied by ResMart LLC constitutes a warranty regarding product performance or use. Any information regarding performance or use is only offered as suggestion for investigation for use, based upon ResMart LLC or other customer experience. ResMart LLC makes no warranties, expressed or implied, concerning the suitability or fitness of any of its products for any particular purpose. It is the responsibility of the customer to determine that the product is safe, lawful and technically suitable for the intended use. The disclosure of information herein is not a license to operate under, or a recommendation to infringe any patents.