

ResMart Ultra HIPS 9-2 - High flow HIPS for injection molding applications

Technical Data Sheet Properties

Physical Property	Value	Test Method
Specific Gravity	1.03	ASTM D 792
Melt Flow Rate	9.0 g/10 min	ASTM D1238
Mold Shrinkage	0.3 - 0.6 %	ASTM D 955

Mechanical Property	Value	Test Method
Tensile Strength	3550 psi	ASTM D 638
Tensile Elongation	50 %	ASTM D 638
Flexural Strength	4260 psi	ASTM D 790
Flexural Modulus	241400 psi	ASTM D 790
Notched Izod Impact (0.125in)	2.0 ft-lbs/in	ASTM D 256

Thermal Property	Value	Test Method
HDT (264 psi) Unannealed	170 °F	ASTM D 648
Vicat Softening Point	206 °F	ASTM D 1525

Regulatory Compliance	Value
FDA Compliance	Yes
RoHS Compliance	Yes

Processing Guidelines	Value
Drying Temperature	180 °F
Drying Time	2 - 3 Hours
Melt Temperature	410 - 480 °F
Mold Temperature	100 - 150 °F

The information provided on this datasheet should only be used as a guideline. Actual lot to lot values will vary.

Disclaimer: No information supplied by ResMart LLC constitutes a warranty regarding product performance or use. Any information regarding performance or use is only offered as suggestion for investigation for use, based upon ResMart LLC or other customer experience. ResMart LLC makes no warranties, expressed or implied, concerning the suitability or fitness of any of its products for any particular purpose. It is the responsibility of the customer to determine that the product is safe, lawful and technically suitable for the intended use. The disclosure of information herein is not a license to operate under, or a recommendation to infringe any patents.