

ResMart ABS VH-0815 BLK - High flow injection molding grade ABS with a UL 94 5VA flammability rating

Technical Data Sheet Properties

Physical Property	Value	Test Method
Specific Gravity	1.15	ASTM D 792
Melt Flow Rate @ 200°C - 5kg	3.8 g/10 min	ASTM D 1238
Mold Shrinkage	0.34 - 0.41 %	ASTM D 955

Mechanical Property	Value	Test Method
Tensile Strength at Yield	5700 psi	ASTM D 638
Tensile Strength at Break	4000 psi	ASTM D 638
Tensile Modulus	290,000 psi	ASTM D 638
Tensile Strain at Break	17 %	ASTM D638
Flexural Strength	8500 psi	ASTM D 790
Flexural Modulus	310,000 psi	ASTM D 790
Notched Izod Impact (0.25in)	4.6 ft-lbs/in	ASTM D 256
Rockwell Hardness (R-Scale)	100	ASTM D 785

Thermal Property	Value	Test Method
HDT (1/4", 264 psi)	171 °F	ASTM D 648
Vicat Softening Temp (50°C/HR)	86 °C	ISO R306B
Flammability @ 1.5mm	V-1	UL 94
Flammability @ 2.0mm	5VB	UL 94
Flammability @ 2.5mm	5VA	UL 94

Processing Guidelines	Value
Drying Temperature	180 °F
Drying Time	2 - 4 Hours
Melt Temperature	420 - 460 °F
Mold Temperature	100 - 180 °F
Injection Pressure	10 - 20 psi

The information provided on this datasheet should only be used as a guideline. Actual lot to lot values will vary.

Disclaimer: No information supplied by ResMart LLC constitutes a warranty regarding product performance or use. Any information regarding performance or use is only offered as suggestion for investigation for use, based upon ResMart LLC or other customer experience. ResMart LLC makes no warranties, expressed or implied, concerning the suitability or fitness of any of its products for any particular purpose. It is the responsibility of the customer to determine that the product is safe, lawful and technically suitable for the intended use. The disclosure of information herein is not a license to operate under, or a recommendation to infringe any patents.