

ResMart Ultra PK6R - Heat stabilized Polyketone resin for injection and extrusion applications

Technical Data Sheet Properties

Physical Property	Value	Test Method
Specific Gravity	1.24	ASTM D 792
Melt Flow Rate @ 240°C - 2.16kg	6.0 g/10 min	ASTM D 1238
Mold Shrinkage	1.5 - 2.3 %	ASTM D 955

Mechanical Property	Value	Test Method
Tensile Strength	8400 psi	ASTM D 638
Tensile Strain at Yield	22 %	ASTM D638
Tensile Strain at Break	300 %	ASTM D638
Flexural Strength	7700 psi	ASTM D 790
Flexural Modulus	195000 psi	ASTM D 790
Notched Izod Impact Strength	4.0 ft-lb/in.	ASTM D256

Thermal Property	Value	Test Method
HDT (66 psi) Unannealed	383 °F	ASTM D 648
HDT (264 psi) Unannealed	215 °F	ASTM D 648
Vicat Softening Point	377 °F	ASTM D 1525

Regulatory Compliance	Value
RoHS Compliance	Yes

Processing Guidelines	Value
Drying Temperature	160 - 180 °F
Drying Time	2 - 4 Hours
Melt Temperature	450 - 470 °F
Mold Temperature	150 - 200 °F
Injection Pressure	10000 - 15000 psi

The information provided on this datasheet should only be used as a guideline. Actual lot to lot values will vary.

Disclaimer: No information supplied by ResMart LLC constitutes a warranty regarding product performance or use. Any information regarding performance or use is only offered as suggestion for investigation for use, based upon ResMart LLC or other customer experience. ResMart LLC makes no warranties, expressed or implied, concerning the suitability or fitness of any of its products for any particular purpose. It is the responsibility of the customer to determine that the product is safe, lawful and technically suitable for the intended use. The disclosure of information herein is not a license to operate under, or a recommendation to infringe any patents.