

**ResMart Plus HDPE 5502- ResMart Plus HDPE 5502**

Technical Data Sheet Properties

Physical Property	Value	Test Method
Melt Flow Rate @ 190°C - 2160g	0.35 g/10min	ASTM D 1238
Tensile Strength	3700 psi	ASTM D 638
Flexural Modulus	185000 Mpsi	ASTM D 790
Specific Gravity	0.955	ASTM D 792

\* Data herein is typical and not to be construed as specifications.

The information provided on this datasheet should only be used as a guideline. Actual lot to lot values will vary.

Disclaimer: No information supplied by ResMart LLC constitutes a warranty regarding product performance or use. Any information regarding performance or use is only offered as suggestion for investigation for use, based upon ResMart LLC or other customer experience. ResMart LLC makes no warranties, expressed or implied, concerning the suitability or fitness of any of its products for any particular purpose. It is the responsibility of the customer to determine that the product is safe, lawful and technically suitable for the intended use. The disclosure of information herein is not a license to operate under, or a recommendation to infringe any patents.