

**ResMart Plus LDPE 920-2- ResMart Plus LDPE 920-2**

Technical Data Sheet Properties

Physical Property	Value	Test Method
Tensile Strength	1600 psi	ASTM D 638
Flexural Strength	30000 psi	ASTM D 790
Specific Gravity	0.92	ASTM D 792
Melt Flow Rate	2.00 g/10 min	ASTM D1238
Density (23°C)	0.92 g/cm <sup>3</sup>	ASTM D1505

\* Data herein is typical and not to be construed as specifications.

Injection Molding Processing Guidelines

Setting	Value
Drying Temperature	175 °F
Mold Temperature	70 - 150 °F
Drying Time	2 Hours
Melt Temperature	380 - 450 °F
Injection Pressure	10000 - 15000 psi

\* Desiccant type dryer required.

The information provided on this datasheet should only be used as a guideline. Actual lot to lot values will vary.

Disclaimer: No information supplied by ResMart LLC constitutes a warranty regarding product performance or use. Any information regarding performance or use is only offered as suggestion for investigation for use, based upon ResMart LLC or other customer experience. ResMart LLC makes no warranties, expressed or implied, concerning the suitability or fitness of any of its products for any particular purpose. It is the responsibility of the customer to determine that the product is safe, lawful and technically suitable for the intended use. The disclosure of information herein is not a license to operate under, or a recommendation to infringe any patents.