

ResMart Ultra CoPP 20-2- Prime FDA Impact Copolymer Polypropylene that provides a good combination of impact and stiffness

Technical Data Sheet Properties

Physical Property	Value	Test Method
Melt Flow Rate @ 230°C - 2160g	20 g/10min	ASTM D 1238
Notched Izod Impact 0.125"	2.0 ft-lbs/in	ASTM D 256
Tensile Strength	3450 psi	ASTM D 638
Tensile Elongation @ Yield	5.1 %	ASTM D 638
HDT (66 psi) Unannealed	220 °F	ASTM D 648
Flexural Modulus	.19 Mpsi	ASTM D 790
Specific Gravity	.902	ASTM D 792

* Data herein is typical and not to be construed as specifications.

Injection Molding Processing Guidelines

Setting	Value
Drying Temperature	175 °F
Mold Temperature	90 - 150 °F
Drying Time	2 Hours
Melt Temperature	375 - 450 °F
Injection Pressure	10000 - 15000 psi

* Desiccant type dryer required.

Regulatory Compliance

Regulatory Compliance	Value
FDA Compliance	Yes
RoHS Compliance	Yes

The information provided on this datasheet should only be used as a guideline. Actual lot to lot values will vary.

Disclaimer: No information supplied by ResMart LLC constitutes a warranty regarding product performance or use. Any information regarding performance or use is only offered as suggestion for investigation for use, based upon ResMart LLC or other customer experience. ResMart LLC makes no warranties, expressed or implied, concerning the suitability or fitness of any of its products for any particular purpose. It is the responsibility of the customer to determine that the product is safe, lawful and technically suitable for the intended use. The disclosure of information herein is not a license to operate under, or a recommendation to infringe any patents.